

PRODUCT DATA SHEET

Purolite® A847DL

Polyacrylic Gel, Weak Base Anion
Resin, Free Base form, Layered Bed
grade

PRINCIPAL APPLICATIONS

- Guard Column for SBA
- Demineralization - High organics water

ADVANTAGES

- Low Rinse Volumes
- Excellent resistance to organic fouling
- Unique resistance against osmotic shock attrition
- Exceptional physical stability
- Efficient regeneration

SYSTEMS

- Layered Beds

REGULATORY APPROVALS

- Kosher Certified

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polyacrylic crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Tertiary Amine
Ionic Form	FB form
Total Capacity	1.6 eq/L (35.0 Kgr/ft ³) (FB form)
Moisture Retention	56 - 62 % (FB form)
Particle Size Range	300 - 630 µm
< 300 µm (max.)	3 %
Uniformity Coefficient (max.)	1.4
Irreversible Swelling (max.)	5 %
Reversible Swelling, FB → Cl ⁻ (max.)	25 %
Specific Gravity	1.08
Shipping Weight (approx.)	665 - 695 g/L (41.6 - 43.4 lb/ft ³)
Temperature Limit	40 °C (104.0 °F) (FB form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

FSU
T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



Americas

T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA

T +44 1443 229334
F +44 1443 227073
europa@purolite.com

Asia Pacific

T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

FSU

T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com