## PRODUCT DATA SHEET

# Macronet™ MN150

Hyper-crosslinked Polystyrenic Macroporous, Adsorbent Resin, Weak Base Functionality, Free Base form

# PRINCIPAL APPLICATIONS

- Sorption
- Hydrophobic organic species separation
- **Decolorization Sweeteners**
- Decolorization Beer Broths
- Porphyrines encapsulation

### **ADVANTAGES**

- High mechanical strength
- High surface area compared to a standard adsorbent
- Dual IEX/hydrobobic interaction

### **REGULATORY APPROVALS**

- IFANCA Halal Certified
- Kosher Certified
- Compliant with FDA Regulation 21 CFR 173.25 for Food Treatment, Ion Exchangers
- Compliant with Europe Resolution ResAP (2004)3
- GMO/TSE/BSE free

## **TYPICAL PACKAGING**

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m3 Supersack
- 42 ft<sup>3</sup> Supersack

# **TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:**

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Tertiary Amine
Ionic Form	FB
Total Capacity	0.2 eq/L (4.4 Kgr/ft³) (Cl¯ form)
Moisture Retention	50 - 58 % (Cl <sup>-</sup> form)
Mean Diameter	535 ± 85 μm
Particle Size Range	300 - 1200 μm
Uniformity Coefficient (max.)	1.4
Reversible Swelling, FB → Cl <sup>-</sup> (max.)	5 %
Pore Volume (min.)	0.6 mL/g
Specific Gravity	1.09
d50, Meso and Macropores (min.)	460 Å
d50, Micropores	14 Å
SBC (max.)	20 %
Surface Area (min.)	800 m²/g
Shipping Weight (approx.)	685 - 720 g/L (42.8 - 45.0 lb/ft³)
Temperature Limit	60 °C (140.0 °F) (FB form)
pH Limits, Stability	0 - 14



Americas T +1 610 668 9090

F +1 610 668 8139 americas@purolite.com **EMEA** T +44 1443 229334 F +44 1443 227073 europe@purolite.com Asia Pacific T +86 571 876 31382 F +86 571 876 31385 asiapacific@purolite.com FSU T +7 495 363 5056 F +7 495 564 8121 fsu@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com

#### EMEA

T +44 1443 229334 F +44 1443 227073 europe@purolite.com

#### Asia Pacific

T +86 571 876 31382 F +86 571 876 31385 asiapacific@purolite.com

#### FSU

T +7 495 363 5056 F +7 495 564 8121 fsu@purolite.com