

## PRODUCT DATA SHEET

# Puromet™ MTS9850

Polyacrylic Macroporous, Polyamine  
Chelating Resin

## PRINCIPAL APPLICATIONS

- Heavy Metals Removal

## ADVANTAGES

- Excellent kinetics
- Excellent mechanical strength
- Excellent resistance to osmotic shock

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polyacrylic crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Polyamine
Ionic Form	FB form
Total Capacity	2.3 eq/L (50.3 Kgr/ft <sup>3</sup> ) (FB form)
Moisture Retention	52 - 57 % (FB form)
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling, FB → Cl <sup>-</sup> (max.)	20 %
Specific Gravity	1.07
Shipping Weight (approx.)	670 - 710 g/L (41.9 - 44.4 lb/ft <sup>3</sup> )
Temperature Limit	40 °C (104.0 °F)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com

**FSU**  
T +7 495 363 5056  
F +7 495 564 8121  
fsu@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



**Americas**

T +1 610 668 9090  
F +1 610 668 8139  
[americas@purolite.com](mailto:americas@purolite.com)

**EMEA**

T +44 1443 229334  
F +44 1443 227073  
[europa@purolite.com](mailto:europa@purolite.com)

**Asia Pacific**

T +86 571 876 31382  
F +86 571 876 31385  
[asiapacific@purolite.com](mailto:asiapacific@purolite.com)

**FSU**

T +7 495 363 5056  
F +7 495 564 8121  
[fsu@purolite.com](mailto:fsu@purolite.com)