PRODUCT DATA SHEET

Purolite® NRW1100

Polystyrenic Gel, Strong Acid Cation Resin, Hydrogen form, Uniform Particle Size, Nuclear Grade

PRINCIPAL APPLICATIONS

- Decontamination Lithiated primary circuits
- Mixed Bed cation component
- Layering Added cation capacity

SYSTEMS

Cation resin vessels

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

TVDICAL	DHYSICAL	& CHEMICAL	CHARACTERISTICS:
ITPICAL	PHISICAL	- a Cheivilcal	CHARACTERISTICS.

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	
Appearance	Spherical Beads	
Functional Group	Sulfonic Acid	
Ionic Form	H ⁺ form	
Total Capacity	2 eq/L (43.7 Kgr/ft³) (H ⁺ form)	
Moisture Retention	46 - 50 % (H ⁺ form)	
Mean Diameter	650 ± 50 μm	
Uniformity Coefficient (max.)	1.2	
Conversion (min.)	99.9 % (H ⁺ form)	
Impurities Iron (max.)	50 ppm	
Impurities Sodium (max.)	40 ppm	
Impurities Heavy Metals (max.)	40 ppm	
Specific Gravity	1.22	
Shipping Weight (approx.)	760 - 800 g/L (47.5 - 50.0 lb/ft³)	
Temperature Limit	120 °C (248.0 °F)	



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com

EMEA

T +44 1443 229334 F +44 1443 227073 europe@purolite.com

Asia Pacific

T +86 571 876 31382 F +86 571 876 31385 asiapacific@purolite.com

FSU

T +7 495 363 5056 F +7 495 564 8121 fsu@purolite.com