

PRODUCT DATA SHEET

Shallow Shell™ SSTPPC8000E

Polystyrenic Gel, Strong Acid Cation
Resin, Sodium form, Shallow Shell™
Technology*, Packed Bed Grade

PRINCIPAL APPLICATIONS

- Demineralization - Potable Water
- Softening - Potable Water

ADVANTAGES

- SST shorter diffusion path benefits:
- Highest regeneration efficiency
- Very low leakage
- Highly resistant to iron fouling
- Lower rinse volumes
- Lower operating costs
- Excellent physical and chemical stability

SYSTEMS

- Potable water treatment
- Packed Bed Systems
- Coflow regenerated systems

REGULATORY APPROVALS

- Certified by the WQA to NSF/ANSI-61 Standard

TYPICAL PACKAGING

- 1 ft³ Sack
- 5 ft³ Sack
- 5 ft³ Drum

* SST® is a registered trademark of Purolite Corporation.

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	Na ⁺
Dry Weight Capacity (min.)	4.0 eq/kg (Na ⁺ form)
Moisture Retention	42 - 48 % (Na ⁺ form)
Mean Diameter	650 ± 50 µm
Uniformity Coefficient (max.)	1.25
Reversible Swelling, Na ⁺ → H ⁺ (max.)	6 %
Specific Gravity	1.2
Shipping Weight (approx.)	775 - 825 g/L (48.4 - 51.6 lb/ft³)
Temperature Limit	100 °C (212.0 °F)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

FSU
T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



Americas

T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA

T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific

T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

FSU

T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com